

RINOCOAT
FOR PAINT APPLICATIONS



			PROPERTIES							APPLICATIONS				
RINOCOAT	Product Code	CI Name & CI No.	Density (gm/cc)	Oil Absorption (g/100gm pig ± 5gm)	Fastness to Acid 5%	Fastness to Alkali 5%	Light Fastness Full Tone	Weather Fastness Full Tone	Heat Stability (°C) 10 Min	Industrial coating	Water Based	Coil Coating	Automotive and Refinish	Powder Coating
RINOCOAT YELLOW														
Rinocoat Yellow 1 G Monoazo Yellow	RY 1001	PY-1	1.5	35	5	5	7	5	180	●	●	-	-	-
Rinocoat Yellow 3 10G Monoazo Yellow	RY 1003	PY-3	1.6	33	5	5	7	5	140	●	●	-	-	-
Rinocoat Yellow 12 OP Diarylide Yellow	RY 1012	PY-12	1.4	40	5	5	6	4	160	●	●	-	-	●
Rinocoat Yellow 13 GRX Diarylide Yellow	RY 1013	PY-13	1.5	34	5	5	6	4	180	●	●	-	-	●
Rinocoat Yellow 65 Monoazo Yellow	RY 1065	PY-65	1.4	41	5	5	7	5	180	●	●	-	-	-
Rinocoat Yellow 74 2GX Monoazo Yellow	RY 1742	PY-74	1.5	30	5	5	7	5	150	●	●	-	-	●
Rinocoat Yellow 74 5GX Monoazo Yellow	RY 1745	PY-74	1.5	35	5	5	6	5	150	●	●	-	-	●
Rinocoat Yellow 83 HR-OP Diarylide Yellow	RY 1083-O	PY-83	1.5	37	5	5	7	5	200	●	●	●	●	●
Rinocoat Yellow 83 HR-T Diarylide Yellow	RY 1083-T	PY-83	1.5	30	5	5	7	5	200	●	●	●	●	-
RINOCOAT ORANGE														
Rinocoat Orange 5 Monoazo à Naphthol	RO 1005	PO-5	1.5	33	5	5	4	3	180	●	●	-	-	-
Rinocoat Orange 13 SC Disazopyrazolone	RO 1013	PO-13	1.5	39	5	4	7	4	200	●	●	-	-	○
Rinocoat Orange 34 GR Disazopyrazolone	RO 1034	PO-34	1.6	35	5	5	5	3	180	●	●	-	-	●
RINOCOAT RED														
Rinocoat Red 3 SC Monoazo à Naphthol	RR 1003	PR-3	1.5	33	5	5	6	4	180	●	●	-	-	-
Rinocoat Red 4 SC Monoazo à Naphthol	RR 1004	PR-4	1.6	33	5	4	6	4	180	●	●	-	-	-
Rinocoat Red 5 Monoazo à Naphthol	RR 1005	PR-5	1.6	33	5	4	6	4	180	●	●	-	-	-
Rinocoat Red 8 F4R Monoazo Naphthol AS	RR 1008	PR-8	1.5	36	4	4	5	3	150	●	●	-	-	-
Rinocoat Red 48:3 2B (Sr) Monoazo BONA	RR 1483	PR-48:3	1.6	36	2	4	6-7	4-5	220	●	●	-	●	○
Rinocoat Red 48:4 2B (Mn) Monoazo BONA	RR 1484	PR-48:4	1.6	36	1	2	4	3	180	●	●	-	●	○
Rinocoat Red Lake 53:1 Monoazo BONA	RR 1531	PR- 53:1	1.6	33	5	4	6	4	180	●	●	-	-	-
Rinocoat Rubine Toner 57:1 Monoazo BONA Ca	RR 1571	PR-57:1	1.5	42	1	3	5	3	180	●	-	-	-	-
Rinocoat Fast Red 112 FGR Monoazo Naphthol AS	RR 1112	PR-112	1.4	35	5	4	7	5	180	●	●	-	-	-
Rinocoat Red 170 F3RK-OP Monoazo Naphthol AS	RR 1703	PR-170	1.5	40	5	5	8	5	200	●	●	-	○	-
Rinocoat Red 170 F5RK Monoazo Naphthol AS	RR 1705	PR-170	1.6	35	5	5	7	5	250	●	●	-	●	-
RINOCOAT BLUE AND GREEN														
Rinocoat Blue 15:0 Phthalocyanine	RB 1150	PB-15:0	1.6	72	5	5	8	5	180	Waterbased textile Application				
Rinocoat Blue 15:1 Phthalocyanine	RB 1151	PB-15:1	1.6	74	5	5	7-8	5	200	●	●	○	●	●
Rinocoat Blue 15:3 Phthalocyanine	RB 1153	PB-15:3	1.6	63	5	5	8	5	200	●	●	○	●	●
Rinocoat Green 7 Phthalocyanine	RG 1007	PG-7	1.6	50	5	5	7-8	5	200	●	●	●	●	●

● Recommended ○ Limited use — Not Recommended

COLORINA INTERNATIONAL LLP

B-101, Varadlaxmi CHS LTD, Gokhale Road, Mulund (East), MUMBAI - 400081, India. ☎ +91 86558 10763

✉ info@colorina.in 🌐 http://www.colorina.in