

RINOPLAST
FOR PLASTIC APPLICATIONS



			PROPERTIES							APPLICATIONS				
RINOPLAST	Product Code	CI Name & CI No.	Density (gm/cc)	Oil Absorption (g/100gm pig ± 5gm)	Fastness to Acid 5%	Fastness to Alkali 5%	Light Fastness-Full Tone	Weather Fastness-Full Tone	Heat Stability (°c) 10 Min	PE	PP Fiber	Engineering Plastics	PET	Nylon 6
RINOPLAST YELLOW														
Rinoplast Yellow 12 OP Diarylide Yellow	RY 2012	PY-12	1.4	40	5	5	4	3	180	●	○	-	-	-
Rinoplast Yellow 13 TR Diarylide Yellow	RY 2013	PY-13	1.3	45	5	4	7	4	220	●	●	●	○	-
Rinoplast Yellow 17 Diarylide Yellow	RY 2017	PY-17	1.3	50	4	4	6	4	240	●	●	●	○	-
Rinoplast Yellow 62 Monoazo Yellow	RY 2062	PY-62	1.7	62	5	4	7	4	240	●	●	●	○	-
Rinoplast Yellow 191 Monoazo Yellow	RY 2191	PY-191	1.4	40	4	3	6-7	4-5	300	●	●	●	-	-
Rinoplast Yellow 180 Monoazo Yellow	RY 2180	PY-180	1.5	50	4	3	6-7	4	290	●	●	●	-	-
RINOPLAST ORANGE														
Rinoplast Orange 13 SC Disazopyrazolone	RO 2013	PO-13	1.2	45	5	5	5	5	220	●	●	●	○	-
Rinoplast Orange 64 Disazopyrazolone	RO 2064	PO-64	1.5	40	5	5	8	5	300	●	●	●	-	-
RINOPLAST RED														
Rinoplast Red 4 SC Monoazo à Naphthol	RR 2004	PR-4	1.5	45	4	3	6	3	180	●	-	-	-	-
Rinoplast Red 8 F4R Monoazo Naphthol AS	RR 2008	PR-8	1.6	50	4	3	5-6	4	180	●	-	-	-	-
Rinoplast Red 48:2 Monoazo BONA	RR 2482	PR-48:2	1.7	45	2	3	7	4	240	●	●	●	-	-
Rinoplast Red 48:3 2B (Sr) Monoazo BONA	RR 2483	PR-48:3	1.7	50	2	3	7	4	240	●	●	●	-	-
Rinoplast Red Lake 53:1 Monoazo BONA	RR 2531	PR - 53:1	1.8	40	4	4	6-7	3-4	240	●	●	●	-	-
Rinoplast Rubine Toner 57:1 Monoazo BONA Ca	RR 2571	PR-57:1	1.5	60	4	4	6-7	4	240	●	●	●	○	-
Rinoplast Fast Red 112 FGR Monoazo Naphthol AS	RR 2112	PR-112	1.5	35	4	5	7	4-5	200	●	●	●	○	-
Rinoplast Red 170 F3RK-OP Monoazo Naphthol AS	RR 2173	PR-170	1.4	45	5	5	7	4	260	●	●	-	-	-
Rinoplast Red 170 F5RK Monoazo Naphthol AS	RR 2175	PR-170	1.4	45	5	5	7	4	260	●	●	-	-	-
RINOPLAST BLUE AND GREEN														
Rinoplast Blue 15:0 Phthalocyanine	RB 2150	PB-15:0	1.6	35	5	5	7	5	180	●	●	●		
Rinoplast Blue 15:1 Phthalocyanine	RB 2151	PB-15:1	1.6	35	5	5	8	5	300	●	●	●	●	●
Rinoplast Blue 15:3 Phthalocyanine	RB 2153	PB-15:3	1.4	40	5	5	7-8	4	300	●	●	●	●	●
Rinoplast Green 7 Phthalocyanine	RG 2007	PG -7	1.6	38	5	5	8	5	300	●	●	●	●	●

● Recommended ○ Limited use — Not Recommended

COLORINA INTERNATIONAL LLP

B-101, Varadlaxmi CHS LTD, Gokhale Road, Mulund (East), MUMBAI - 400081, India. ☎ +91 86558 10763

✉ info@colorina.in 🌐 http://www.colorina.in